



MACHINING CONDITIONS

VBMT 160408 NN LT 1000

T0001944

Material Group	Lamina Group	Material Example	Hardness	D.O.C		Feed		Amax		Vc		Advised D.O.C	Advised Feed [mm/t]	Advised Vc [m/min]
				min[mm]	max[mm]	min[mm/t]	max [mm/t]	[mm^2]	min [m/min]	max [m/min]	[mm]			
Steel	Non Alloyed	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.5	3.5	0.19	0.4	1.26	180	330	2.5	0.32	240	
			190 HB	0.5	3.5	0.19	0.4	1.26	180	280	2.5	0.3	220	
			250 HB	0.5	3.5	0.19	0.36	1.05	180	250	2.5	0.28	200	
Steel	Low Alloyed	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.5	2.8	0.19	0.36	0.84	120	250	2.5	0.27	180	
			280 HB	0.5	2.8	0.16	0.32	0.84	120	210	2.5	0.26	150	
			180 HB	0.5	3.5	0.19	0.36	0.84	120	280	2.5	0.27	200	
			350 HB	0.5	2.5	0.16	0.32	0.7	120	180	2.2	0.26	130	
Stainless Steel	High Alloyed	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.5	2.8	0.16	0.32	0.84	70	190	2.1	0.26	140	
			280 HB	0.5	2.8	0.16	0.32	0.84	70	150	2.1	0.26	120	
			320 HB	0.5	2.1	0.16	0.28	0.56	70	130	1.8	0.24	100	
			350 HB	0.5	2.1	0.16	0.28	0.56	70	110	1.8	0.24	90	
Stainless Steel	Austentic	304, 316, X5CrNi18-9	180 HB	0.5	3.5	0.18	0.32	0.84	170	270	2.5	0.21	190	
	Duplex		240 HB	0.5	3.5	0.18	0.32	0.7	160	220	2.5	0.19	170	
Cast Iron	Grey	X2CrNiN23-4, S31500	290 HB	0.5	2.8	0.16	0.28	0.56	80	150	2.1	0.2	100	
			310 HB	0.5	2.8	0.16	0.28	0.56	70	140	2.1	0.2	90	
			200 HB	0.5	3.5	0.16	0.32	0.49	170	250	2.1	0.17	190	
			42 HRc	0.5	2.8	0.16	0.32	0.49	120	190	1.8	0.17	130	
Cast Iron	Malleable & Nodular	GG20, GG40, EN-GJL-250, N030B	150 HB	0.5	3.5	0.14	0.48	1.4	170	250	2.5	0.3	200	
			200 HB	0.5	3.5	0.14	0.48	1.26	160	230	2.5	0.3	180	
			250 HB	0.5	3.5	0.14	0.44	1.26	150	210	2.5	0.3	160	
Niti Alloy	Fe, Ni & Co Based	GGG40, GGG70, 50005	150 HB	0.5	3.5	0.14	0.4	1.05	120	250	2.5	0.26	180	
			200 HB	0.5	3.5	0.14	0.4	0.91	120	230	2.5	0.26	160	
			250 HB	0.5	3.5	0.14	0.4	0.84	120	190	2.5	0.26	140	
Niti Alloy	Ti Based	Incoloy 800	T40	-	0.5	2.1	0.18	0.28	0.49	30	50	1.6	0.24	30
			Inconel 700	240 HB	0.5	2.1	0.18	0.28	0.49	30	50	1.6	0.24	30
Hardened Materials	Steel Chilled Cast Iron White Cast Iron	Stellite 21	350 HB	0.5	2.1	0.18	0.28	0.49	30	40	1.6	0.24	30	
			TiAl6V4	-	0.5	2.5	0.18	0.32	0.56	50	70	1.6	0.28	55
			G-X300CrMo15	55 HRc	0.5	1.1	0.1	0.16	0.21	30	50	0.8	0.13	40
			Ni-Hard 2	400 HB	0.5	1.4	0.1	0.2	0.28	40	60	1.2	0.15	50
			X100CrMo13, 440C, G-X260NiCr42	45 HRc	0.5	1.8	0.1	0.24	0.42	50	100	1.6	0.21	80
Aluminium	Al (>8%Si)	AISI12	50 HRc	0.5	1.4	0.1	0.2	0.28	40	90	1.2	0.17	70	
			55 HRc	0.5	1.1	0.1	0.16	0.21	40	80	0.8	0.15	60	
Aluminium	Al (>8%Si)	AISI12	130 HB	0.5	4.2	0.18	0.48	1.26	200	400	2.5	0.34	280	

