



MACHINING CONDITIONS

VNMG 160404 NN LT 1000

T0001947

Material Group	Lamina Group	Material Example	Hardness	D.O.C		Feed		Amax		Vc		Advised D.O.C	Advised Feed [mm/t]	Advised Vc [m/min]	
				min[mm]	max[mm]	min[mm/t]	max [mm/t]	[mm^2]	min [m/min]	max [m/min]	[mm]				
Steel	Non Alloyed	1	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.3	3	0.11	0.23	0.6	180	330	2	0.18	300	
				190 HB	0.3	2.5	0.11	0.22	0.52	180	280	2	0.18	260	
				250 HB	0.3	2.5	0.11	0.2	0.48	180	250	2	0.18	240	
	Low Alloyed	2	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.3	2.5	0.1	0.2	0.48	120	250	2	0.14	240	
				280 HB	0.3	2	0.1	0.18	0.4	120	210	2	0.13	200	
				180 HB	0.3	2.5	0.1	0.2	0.5	120	280	2	0.14	260	
				350 HB	0.3	2	0.1	0.18	0.36	120	180	2	0.13	180	
	High Alloyed	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.3	2.5	0.09	0.18	0.4	70	190	1.7	0.1	180	
				280 HB	0.3	2.5	0.09	0.16	0.4	70	150	1.7	0.1	140	
				320 HB	0.3	2	0.09	0.14	0.32	70	130	1.7	0.1	120	
				350 HB	0.3	2	0.09	0.14	0.26	70	110	1.7	0.1	110	
Stainless Steel	Austentic	4	304, 316, X5CrNi18-9	180 HB	0.3	2.5	0.08	0.18	0.32	170	270	2	0.09	260	
	240 HB	0.3		2.5	0.08	0.18	0.26	160	220	2	0.08	210			
	Duplex	5	X2CrNiN23-4, S31500	290 HB	0.3	2	0.08	0.14	0.2	80	150	1.7	0.08	140	
	Ferritic & Martensitic	6	410, X6Cr17, 17-4 PH, 430	310 HB	0.3	2	0.08	0.14	0.2	70	140	1.7	0.08	140	
	200 HB	0.3		2.5	0.08	0.18	0.32	170	250	1.7	0.09	240			
Cast Iron	Grey	7	GG20, GG40, EN-GJL-250, N030B	42 HRc	0.3	2	0.08	0.16	0.26	120	190	1.5	0.08	180	
	150 HB	0.3		3	0.08	0.2	0.64	170	250	2	0.18	240			
	200 HB	0.3		3	0.08	0.2	0.6	160	230	2	0.18	220			
	Malleable & Nodular	8	GGG40, GGG70, 50005	250 HB	0.3	3	0.08	0.2	0.6	150	210	2	0.18	200	
				150 HB	0.3	2.5	0.08	0.18	0.48	120	250	2	0.13	240	
				200 HB	0.3	2.5	0.08	0.18	0.4	120	230	2	0.13	220	
NI Ti Alloy	Fe, Ni & Co Based	9	Incoloy 800, Inconel 700, Stellite 21	250 HB	0.3	2.5	0.08	0.18	0.4	120	190	2	0.13	180	
				350 HB	0.3	2	0.09	0.15	0.26	20	50	1.3	0.1	35	
				T40	-	0.3	2	0.09	0.14	0.26	40	60	1.3	0.1	50
Hardened Materials	Ti Based	10	TiAl6V4, G-X300CrMo15, Ni-Hard 2, X100CrMo13, 440C, G-X260NiCr42	TiAl6V4	-	0.3	2	0.09	0.16	0.32	50	70	1.3	0.14	60
				G-X300CrMo15	55 HRc	0.3	1.4	0.05	0.09	0.13	30	50	0.9	0.06	40
				Ni-Hard 2	400 HB	0.3	1.6	0.05	0.12	0.17	40	60	1.1	0.1	50
				45 HRc	0.3	1.8	0.05	0.12	0.2	50	100	1.4	0.1	90	
				50 HRc	0.3	1.5	0.05	0.1	0.17	40	90	1.1	0.08	80	
Aluminium	AI (>8%Si)	12	AISI12	55 HRc	0.3	1.4	0.05	0.09	0.13	40	80	0.9	0.06	70	
				130 HB	0.3	4	0.1	0.3	0.7	200	400	2	0.23	350	

