



MACHINING CONDITIONS

WNMG 060408 NX LT
1000

T0003014

Material Group	Lamina Group	Material Example	Hardness	D.O.C		Feed		Amax [mm^2]	Vc		Advised D.O.C [mm]	Advised Feed [mm/t]	Advised Vc [m/min]
				min[mm]	max[mm]	min[mm/t]	max [mm/t]		min [m/min]	max [m/min]			
Steel	Non Alloyed	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.5	2.5	0.18	0.5	1.13	180	330	1.8	0.36	240
			190 HB	0.5	2.5	0.18	0.5	1.13	180	280	1.8	0.33	220
			250 HB	0.5	2.5	0.18	0.45	0.95	180	250	1.8	0.31	200
Steel	Low Alloyed	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	230 HB	0.5	2	0.18	0.45	0.76	120	250	1.8	0.3	180
			280 HB	0.5	2	0.16	0.4	0.76	120	210	1.8	0.29	150
			180 HB	0.5	2.5	0.18	0.45	0.76	120	280	1.8	0.3	200
			350 HB	0.5	1.8	0.16	0.4	0.63	120	180	1.6	0.29	130
Steel	High Alloyed	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.5	2	0.16	0.4	0.76	70	190	1.5	0.29	140
			280 HB	0.5	2	0.16	0.4	0.76	70	150	1.5	0.29	120
			320 HB	0.5	1.5	0.16	0.35	0.5	70	130	1.3	0.27	100
			350 HB	0.5	1.5	0.16	0.35	0.5	70	110	1.3	0.27	90
Stainless Steel	Austentic	304, 316, X5CrNi18-9	180 HB	0.5	2.5	0.18	0.4	0.76	170	270	1.8	0.24	190
			240 HB	0.5	2.5	0.18	0.4	0.63	160	220	1.8	0.21	170
Stainless Steel	Duplex	X2CrNiN23-4, S31500	290 HB	0.5	2	0.16	0.35	0.5	80	150	1.5	0.23	100
			310 HB	0.5	2	0.16	0.35	0.5	70	140	1.5	0.23	90
Steel	Ferritic & Martensitic	410, X6Cr17, 17-4 PH, 430	200 HB	0.5	2.5	0.16	0.4	0.44	170	250	1.5	0.19	190
			42 HRc	0.5	2	0.16	0.4	0.44	120	190	1.3	0.19	130
Cast Iron	Grey	GG20, GG40, EN-GJL-250, N030B	150 HB	0.5	2.5	0.13	0.6	1.26	170	250	1.8	0.33	200
			200 HB	0.5	2.5	0.13	0.6	1.13	160	230	1.8	0.33	180
			250 HB	0.5	2.5	0.13	0.55	1.13	150	210	1.8	0.33	160
Steel	Malleable & Nodular	GGG40, GGG70, 50005	150 HB	0.5	2.5	0.13	0.5	0.95	120	250	1.8	0.29	180
			200 HB	0.5	2.5	0.13	0.5	0.82	120	230	1.8	0.29	160
			250 HB	0.5	2.5	0.13	0.5	0.76	120	190	1.8	0.29	140
NTT Alloy	Fe, Ni & Co Based	Incoloy 800, Inconel 700, Stellite 21	240 HB	0.5	1.5	0.18	0.35	0.44	30	50	1.2	0.27	30
			250 HB	0.5	1.5	0.18	0.35	0.44	30	50	1.2	0.27	30
			350 HB	0.5	1.5	0.18	0.35	0.44	30	40	1.2	0.27	30
NTT Alloy	Ti Based	T40, TiAl6V4	-	0.5	1.5	0.18	0.35	0.44	40	60	1.2	0.29	45
			-	0.5	1.8	0.18	0.4	0.5	50	70	1.2	0.31	55
Harden Materials	Steel Chilled Cast Iron White Cast Iron	G-X300CrMo15, Ni-Hard 2, X100CrMo13, 440C, G-X260NiCr42	55 HRc	0.5	0.8	0.1	0.2	0.19	30	50	0.6	0.14	40
			400 HB	0.5	1	0.1	0.25	0.25	40	60	0.9	0.17	50
			45 HRc	0.5	1.3	0.1	0.3	0.38	50	100	1.2	0.24	80
			50 HRc	0.5	1	0.1	0.25	0.25	40	90	0.9	0.19	70
			55 HRc	0.5	0.8	0.1	0.2	0.19	40	80	0.6	0.17	60
Aluminum	Al (>8%Si)	AISI12	130 HB	0.5	3	0.18	0.6	1.13	200	400	1.8	0.38	280

